

BLANK PAGE



Indian Standard

SPECIFICATION FOR HANDLOOM COTTON SPONGE CLOTH, GREY, STRIPED OR CHECKED

(First Revision)

First Reprint JANUARY 1998

UDC 677.21.074.164.2/.3

© Copyright 1987

BUREAU OF INDIAN STANDARDS MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG NEW DELHI 110002

Indian Standard

SPECIFICATION FOR HANDLOOM COTTON SPONGE CLOTH, GREY, STRIPED OR CHECKED

(First Revision)

Handloom and Khadi Sectional Committee, TDC 13

Chairman

Representing

DEVELOPMENT COMMISSIONER FOR HANDLOOMS

Development Commissioner for Handlooms, New Delhi

Vice-Chairman

DIRECTOR OF HANDLOOMS AND TEXTILES

Directorate of Handlooms and Textiles, Government of Tamil Nadu, Madras

Members

JOINT DIRECTOR OF HANDLOOMS
AND TEXTILES (Alternate to

Director of Handlooms and Textiles)

SHRI A. T. BASAK

Directorate General of Supplies and Disposals (Inspection Wing), New Delhi

SHRI B. D. DUBE (Alternate)
SHRI P. K. DAS

Directorate of Handlooms and Textiles Government of West Bengal, Calcutta

SHRI SAMIR MUKHERJEE (Alternate)

SHRI O. P. DHAWAN
Silk and Rayon Textiles Export Promotion
Council, Bombay

SHRI L. DESI GOWDA

Indian Institute of Handloom Technology,

Shri Q. M. Humayun

National Handloom Development Corporation Ltd, Lucknow

SHRI D. JAYARAMAIAH

Development Commissioner for Handlooms, New Delhi

DR M. N. U. KURUP Ministry of Defence (DGI)

SHRI R. B. NASEKAR (Alternate)

(Continued on page 2)

© Copyright 1987 BUREAU OF INDIAN STANDARDS

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

(Continued from page 1)

Members

Representing

SHRI T. MAHADEVAN	The Handloom Export Promotion Council,				
SHRI B. N. MEHTA	Directorate of Industries, Government of Haryana, Chandigath				
SHRI C. R. YADAV (Alternate) SHRI K. S. MURTHI The Khadi and Village Industries Commission, Bombay					
Supe R. S. Kulkarni (Alter	nate)				

SHRI P. VIJAYAN (Alternate)

Kerala State Handloom Development Corporation Limited, Cannanore All India Federation of Co-op Spinning Mills

SHRI R. G. OWALEKAR SHRI M. G. RAJAN

SIRI N. BALAKRISHNAN NAIR

Ltd. Eombay Textiles Committee, Bombay

SHRI A. S. RAMA RAO (Alternate) SHRI K. RANGANATHAN

The South India Textiles Research Association. Coimt atore

SHRIS. RANGARAIAN SHRI H. R. RAO REGIONAL MANAGER

The Handicrafts and Handlooms Exports
Corporation of India, Madras The Silk and Art Silk Mills' Research Association, Bombay Andhra Pradesh State Handloom Weavers' Co-operative Society Ltd, Vijayawada

REPRESENTATIVE REPRESENTATIVE REPRESENTATIVE

Bhubaneshwar J & K State Handloom Development Corp Ltd, Srinagar The Director of Handlooms, Govt of Assam.

The Director of Handlooms, Govt of Orissa,

REPRESENTATIVE SHRI K. K. ROHTAGI SHRI M. P. SHARMA (Alternate)

Apparels Export Promotion Council, New Delhi Government of Uttar Pradesh

All India Handloom Fabrics Marketing Co-THE SECRETARY SHRI A. RAJAMANI (Alternate I)

The Tamil Nadu Handloom Weavers' Cooperative Society Ltd, Madras

SHRI D. SENGUPTA (Alternate II) SENIOR EXECUTIVE & SPECIAL OFFICER SENIOR MANAGER (DESIGN &

PRODUCT DEVELOPMENT) (Alternate)

SHRI R. I. MIDHA, Director (Tex)

Director General, BIS (Ex-officio Member)

operative Society Ltd, Bombay

Secretary

Guwahati

SHRI P. BHATNAGAR Deputy Director (Tex), BIS

(Continued on page 8)

Indian Standard

SPECIFICATION FOR HANDLOOM COTTON SPONGE CLOTH, GREY. STRIPED OR CHECKED

(First Revision)

0. FOREWORD

- 0.1 This Indian Standard (First Revision) was adopted by the Bureau of Indian Standards on 11 May 1987, after the draft finalized by the Handloom and Khadi Sectional Committee had been approved by the Textile Division Council.
- 0.2 This standard, first published in 1956, has been revised in order to make it up-to-date in respect of the following changes:
 - a) Yarn conforming to IS: 171-1985* has been recommended;
 - b) Clauses on inspection, marking and packing have been included; and
 - c) Latest versions of Indian Standards on test methods have been specified.
- 0.3 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test, shall be rounded off in accordance with 1S: 2-1960†. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 This standard prescribes the constructional particulars and other requirements of three varieties of handloom cotton sponge cloth, grey, striped or checked.

^{*}Specification for cotton and cotton regenerated cellulosic fibre blended grey yarn (third revision).

[†]Rules for rounding off numerical values (revised).

1.2 This standard does not specify the general appearance, lustre, feel, finish or colour and their combination in striped or checked cloth.

2. MANUFACTURE

- 2.1 Yarn The cotton yarn used in the manufacture of cloth shall conform to the requirements of IS: 171-1985*.
 - 2.1.1 The warp yarn shall not be sized before weaving.
- 2.2 Cloth Each cut end of the sponge cloth shall be hemmed to a depth of not less than 1 cm, the raw edges having a turn in of 10 mm before the hem is formed. Cotton sewing thread conforming to variety number 31 of IS: 1720-1978† shall be used in hemming and number of stitches shall be at least 40 per decimetre.

3. REQUIREMENTS

- 3.1 The cloth shall conform to the constructional requirements and other characteristics as given in Tables 1 and 2.
- 3.2 If in order to illustrate or specify the indeterminable characteristics, such as general appearance, lustre, feel, and shade of the cloth, a sample has been agreed upon and sealed, the supply shall be in conformity with the sample in such respects.
- 3.2.1 The custody of the sealed sample shall be a matter of prior agreement between the buyer and the seller.

4. INSPECTION

- 4.1 The cloth when visually inspected should be reasonably free from the following defects:
 - a) Weft crack or more than two missing picks across the width;
 - b) Prominently noticeable weft bar due to the difference in raw material, count, twist, lustre, colour, shade, etc;
 - c) More than two adjacent ends running parallel, broken or missing and extending beyond 15 cm;
 - d) Prominent selvedge defects;
 - e) Noticeable warp or weft float;
 - f) Noticeable hole, cut or tear up to 3 mm in size;

^{*}Specification for cotton and cotton regenerated cellulosic fibre blended grey yarn (third revision).

[†]Specification for cotton sewing threads (second revision).

TABLE 1 CONSTRUCTIONAL PARTICULARS OF HANDLOOM COTTON SPONGE CLOTH, GREY, STRIPED OR CHECKED

(Clause 3.1)

Variety No.	Count of Yarn (For Guidan	(APPROX) ce Only)	Ends	Picks	Weight	LENGTH	WIDTE	I WEAVE
	Warp	Weft						
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)
	tex (Cotton Count)	tex (Cotton Count)	per dm	per dm	g/m²			
1.	295 tex (or 2s)	295 tex (or 2s)	50	50	315			2/2 twill
2.	60 tex \times 2 (or $10^{2}/2$)	394 tex (or 1.5s)	50	70	390	As agre		2/2 twill
3.	30 tex × 2 (or 20 ^s /2)	148 tex (or 4s)	40	30 (double)	270			One and one leno
Toleran		_	± 5	±5	<u>+</u> 5	-2	-2	_
Method test	of —		IS: 1963-1981	•	IS : 1964- 1970	IS : 195	4-1969‡	Visual

Note 1 — The usual width and corresponding length of sponge cloth are given below:

Width, cm	Length, cm
18	18
18	21
21	21

^{*}Methods for determination of threads per unit length in woven fabrics (second revision).

[†]Methods for determination of weight per square metres and weight per linear metre of fabrics (first revision).

tMethods for determination of length and width of fabrics (first revision).

TABLE 2 REQUIREMENTS OF HANDLOOM COTTON SPONGE CLOTH, GREY, STRIPED OR CHECKED

(Clause 3.1)

St No.	CHARACTER:STIC	REQUIREMENT	METHOD OF TEST
i)	Colour fastness (for striped or checked cloth only)		
	a) Light	4 or better	IS: 686-1985* or
			IS: 2454-1985†
	b) Washing: Test 4		IS: 765-1979‡
	i) Change in colour	4 or better	·
	ii) Staining on coaton	4 or better	
ii)	Scouring loss, percent, Max	5	1S: 1383-1977§ (mild method)

^{*}Method for determination of colour fastness of textile materials to daylight (first revision).

+Method for determination of colour fastness of textile materials to artificial light (xenon lamp) (first revision).

tMethod for determination of colour fastness of textile materials to washing: Test 4 (second revision).

§Method for determination of scouring loss in grey and finished cotton textile materials (first revision).

- g) Noticeable oil or other stains;
- h) Smash rupturing the texture of the fabric; and
- j) Prominently noticeable dyeing defects (bars, streaks and patches, etc).
- 41.1 A reference may be made to IS: 4125-1967* for details of these defects.

5. MARKING

- 5.1 The cloth shall be suitably marked or labelled with the following information:
 - a) Name of the material, and variety number;
 - b) Manufacturer's name, initials or trade-mark;
 - c) Month and year of manufacture; and
 - d) Length and width of piece.

^{*}Glossary of terms pertaining to defects in fabrics.

5.1.1 The cloth may also be marked with the Standard Mark.

Note — The use of the Standard Mark is governed by the provisions of the Bureau of Indian Standards Act, 1986 and the Rules and Regulations made thereunder. The Standard Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well defined system of inspection, testing and quality control which is devised and supervised by BIS and operated by the producer. Standard marked products are also continuously checked by BIS for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the Standard Mark may be granted to manufacturers or producers, may be obtained from the Bureau of Indian Standards.

6. PACKING

6.1 Unless otherwise agreed upon by the buyer and the seller, the cloth shall preferably be packed in bales or cases in conformity with the procedure laid down either in IS: 1347-1972* or IS: 293-1980†.

7. SAMPLING

- 7.1 The scale of sampling and criteria for conformity as given in IS: 3919-1966‡ shall be followed in respect of physical characteristics, namely, ends and picks, weight, length, width, and weave.
- 7.2 The scale of sampling and criteria for conformity as given in IS: 5463-1969§ shall be followed in respect of the chemical requirements of colour fastness and scouring loss.

^{*}Code for inland packing of cotton cloth and yarn (first revision).
†Code for seaworthy packaging of cotton yarn and cloth (third revision).
†Method for sampling cotton fabrics for determination of physical characteristics.
§Method for sampling of cotton fabrics for chemical tests.

(Continued from page 2)

Handloom and Khadi Cotton Cloth Subcommittee, TDC 13:1

Convener

Representing

DIRECTOR, INDIAN INSTITUTE OF HANDLOOM TECHNOLOGY, VARANASI Development Commissioner for Handlooms, New Delhi

Members

SHRI A. T. BASAK

Directorate General of Supplies and Disposals (Inspection Wing), New Delhi

SHRI B. D. DUBE (Alternate)
SHRI P. K. DAS

Directorate of Handlooms and Textiles, Government of West Bengal, Calcutta

SHRI SAMIR MUKHERJEE (Alternate)

SHRI L. DESI GOWDA

Development Commissioner for Handlooms,
New Delhi

SHRI K. K. ROHATGI

Government of Uttar Pradesh

SHRI M. P. SHARMA (Alternate)
SHRI B. R. KAUSHIK

Textiles Committee, Bombay Ministry of Defence (DGI)

DR M. N. U. KURUP N. SHRI N. K. NAGPAL (Alternate)

SHRI C. V. PRABHAKARAN
The Khadi and Village Industries Commission,
Bombay

SHRI M. V. RAMACHANDRA (Alternate)

SHRI S. RANGARAJAN The Handicrafts and Handlooms Exports
Corporation of India Ltd, Madras

SENIOR EXECUTIVE AND SPECIAL OFFICER

The Tamil Nadu Handloom Weavers' Cooperative Society Ltd, Madras

SENIOR MANAGER (DESIGN AND

PRODUCT DEVELOPMENT) (Alternate)

SHRI T. O. THOMAS

Kerala State Handloom Weavers' Co-operativ
Society Ltd, Trivandrum

BUREAU OF INDIAN STANDARDS

BANGALORE 560002

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

Telephones: 323 0131, 323 3375, 323 9402

Fax: 91 11 3234062, 91 11 3239399, 91 11 3239382

	Telegrams : Manaksanstha (Common to all Offices)	
Central Laboratory:		Telephone
Plot No. 20/9, Site IV, Sahibabad Industrial Area, Sahibabad 201	010	8-77 00 32
Regional Offices:		
Central: Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DEL	.HI 110002	323 76 17
*Eastern: 1/14 CIT Scheme VII M, V.I.P. Road, Maniktola, CALCU	TTA 700054	337 86 62
Northern: SCO 335-336, Sector 34-A, CHANDIGARH 160022		60 38 43
Southern : C.I.T. Campus, IV Cross Road, CHENNAI 600113		235 23 15
†Western : Manakalaya, E9, Behind Marol Telephone Exchange, MUMBAI 400093	Andheri (East),	832 92 95
Branch Offices::		
'Pushpak', Nurmohamed Shaikh Marg, Khanpur, AHMEDABAD 3	380001	550 13 48
‡Peenya Industrial Area, 1st Stage, Bangalore-Tumkur Road, BANGALORE 560058		839 49 55
Gangotri Complex, 5th Floor, Bhadbhada Road, T.T. Nagar, BHC	DPAL 462003	55 40 21
Plot No. 62-63, Unit VI, Ganga Nagar, BHUBANESHWAR 75100	1	40 36 27
Kalaikathir Buildings, 670 Avinashi Road, COIMBATORE 641037	7	21 01 41
Plot No. 43, Sector 16 A, Mathura Road, FARIDABAD 121001		8-28 88 01
Savitri Complex, 116 G.T. Road, GHAZIABAD 201001		8-71 19 96
53/5 Ward No.29, R.G. Barua Road, 5th By-lane, GUWAHATI 78	1003	54 11 37
5-8-56C, L.N. Gupta Marg, Nampally Station Road, HYDERABAI	D 500001	20 10 83
E-52, Chitaranjan Marg, C- Scheme, JAIPUR 302001		37 29 25
117/418 B, Sarvodaya Nagar, KANPUR 208005		21 68 76
Seth Bhawan, 2nd Floor, Behind Leela Cinema, Naval K LUCKNOW 226001	ishore Road,	23 89 23
NIT Building, Second Floor, Gokulpat Market, NAGPUR 440010		52 51 71
Patliputra Industrial Estate, PATNA 800013		26 23 05
Institution of Engineers (India) Building 1332 Shivaji Nagar, PUN	E 41 1005	32 36 35
T.C. No. 14/1421, University P. O. Palayam, THIRUVANANTHAPUR	AM 695034	6 21 17
*Sales Office is at 5 Chowringhee Approach, P.O. Princep Street CALCUTTA 700072		27 10 85
†Sales Office is at Novelty Chambers, Grant Road, MUMBAI 400	007	309 65 28
\$Sales Office is at 'F' Block, Unity Building, Narashimaraja Squar	re,	222 39 71